

PCT

WORLD INTELLECTUAL PROPERTY
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER 1

(51) International Patent Classification: C01G 23/07, C01B 13/28, C01G 19/02, C01B 33/00		(11) Int. No. 9606803A1
A1		(43) International Publication Date: 7 March 1996 (07.03.96)
(21) International Application Number: PCT/US95/10641		(84) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.
(23) International Filing Date: 25 August 1995 (25.08.95)		
(30) Priority Data: 299,284 31 August 1994 (31.08.94) US 373,980 18 January 1995 (18.01.95) US 488,694 8 June 1995 (08.06.95) US		
(71) Applicant: UNIVERSITY OF CINCINNATI [US/US]; Mail Location 0529, 201 Wherry Hall, Cincinnati, OH 45267-0529 (US). (72) Inventors: PRATSINIS, Sotiris, Emmanuel; 8243 Farwick Court, Cincinnati, OH 45249 (US). VEMURY, Srinivas; 2920 Scioto Street, Cincinnati, OH 45219 (US). POTOU, George, P.; 539 Lowell Avenue #4, Cincinnati, OH 45290 (US). GUTSCH, Andreas; Soldenwehstrasse 16, D-76128 Karlsruhe (DE). (74) Agents: GOLDSTEIN, Steven, J. et al.; Frost & Jacobs, 2500 PNC Center, 201 E. Fifth Street, Cincinnati, OH 45202 (US).		
(54) Title: PROCESS FOR PRODUCING CERAMIC POWDERS, ESPECIALLY TITANIUM DIOXIDE USEFUL AS A PHOTOCATALYST		
(57) Abstract		
<p>A gas phase process for the production of titanium dioxide powders having well-controlled crystalline and surface area characteristics is disclosed. In this process, which is preferably carried out in a laminar diffusion flame reactor, vapor phase $TiCl_4$ and oxygen are mixed in a reaction area which is heated externally. The titanium dioxide powder formed is then collected. It is preferred that the heat source used be a hydrocarbon fueled (e.g., methane) flame. Optionally, a vapor phase dopant (such as $SiCl_4$) may be added to the reaction mixture to desirably affect the physical properties of the titanium dioxide produced. In a particularly preferred embodiment, a corona electric field is positioned across the area where the combustion reaction takes place (i.e., the reaction area). High anatase, high surface area titanium dioxide powders made by this process are excellent photocatalysts. The products of this process and the use of those products as photocatalysts are also disclosed. This process is also useful for producing other ceramic powders (such as silicon dioxide and tin oxide), as well as pure metallic or alloy powders.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritius
AU	Australia	GD	Grenada	MW	Malawi
BB	Barbados	GH	Ghana	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IL	Israel	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LR	Sierra Leone	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

5
PROCESS FOR PRODUCING CERAMIC
POWDERS, ESPECIALLY TITANIUM
DIOXIDE USEFUL AS A PHOTOCATALYST

10
SOTIRIS EMMANUEL PRATSINIS
SRINIVAS VEMURY
GEORGE P. FOTOU
ANDREAS GUTSCH

15
CROSS-REFERENCE TO RELATED APPLICATION

This application is a continuation-in-part of U.S. patent application Serial No. 08/373,980, filed January 18, 1995, which is a continuation-in-part of U.S. patent application Serial No. 08/299,204, filed August 31, 1994.

20
CONTRACTUAL ORIGIN OF THE INVENTION

The United States Government has rights in this invention pursuant to Contract No. CTS 8957042 between the National Science Foundation and the University of Cincinnati.

25
TECHNICAL FIELD

30
This development relates to a vapor phase process for the production of titanium dioxide, silicon dioxide and aluminum oxide powders and other ceramic powders having well-controlled crystalline and surface area characteristics. The materials produced are especially useful as catalysts in photochemical reactions. The process is also useful for producing metallic and alloy powders.

35
BACKGROUND OF THE INVENTION

Titanium dioxide (titania) is extensively used in pigments, inorganic membranes, semi-conductors, and as a photocatalyst in gas and water purification processes. More than two million tons of titanium dioxide are produced annually;

- 2 -

most of it is manufactured by aerosol processes which provide the advantages of small particle size, narrow size distribution, nearly spherical particles and high purity. Aerosol processes also are energy efficient and avoid the treatment of large liquid volumes associated with traditional wet chemistry processes. On the other hand, conventional aerosol processes are very complex and involve many physicochemical phenomena and mechanisms, such as chemical reaction, particle nucleation, condensation, coagulation, aggregation, heat and mass transfer, and thermophoresis. The fundamentals of these processes are not well understood and, as a result, the processes are difficult to control precisely. This makes design, operation and control of industrial reactors to carry out these processes more of an art than a science, relying heavily on experience and empiricism.

The use of photocatalysis as a purification process for both gas and liquid media has been of growing interest over the past decade. The photocatalytic destruction of organic contaminants is simple, low cost and fast and, therefore, attractive for a variety of purification applications. This process involves illumination of catalytic particles with near UV-light to promote photoexcitation of valence band electrons and holes. These electrons and holes migrate to the surface of the catalytic particles and participate in reduction/oxidation (redox) reactions with adsorbed species. These redox reactions produce highly reactive hydroxyl radicals which are responsible for the oxidation and in some cases the mineralization (complete oxidation to carbon dioxide, water and/or HCl) of the organic species. Among the oxide semiconductors which have been used for the photocatalytic destruction of organic pollutants, the anatase crystalline phase of titanium dioxide is the most effective because of its high photoactivity and stability.

Much of the current work on photocatalysis has been done using commercially available titanium dioxide powders. Though these powders are, in some cases, treated to improve their photocatalytic properties, they are generally not originally produced for this application. As a result, the most important properties for photocatalysis, i.e., specific surface area and crystalline phase composition, are not generally optimized during powder manufacture. Further, as

discussed above, many of the processes currently used to produce titanium dioxide are only able to control such characteristics as surface area and phase composition with relative difficulty and little precision.

5 It was in this context that the present invention was made. This invention provides an effective, easily controlled process for preparing titanium dioxide (and other ceramic) powders. Particularly, the present invention allows for the effective controlling of the level of anatase phase and the surface area of the powder formed. By being able to vary and optimize anatase content and surface
10 area independently of each other, with relative ease, the materials produced are useful for any use of titanium dioxide and are particularly useful as catalysts for photooxidation reactions.

 Formenti, M., et al, in *Acrosols and Atmospheric Chemistry*, G.M. Hidy, ed., Academic Press, New York, pages 45-55 (1972), prepared titanium dioxide
15 particles from the oxidation of $TiCl_4$ in an oxygen-hydrogen diffusion flame. $TiCl_4$ was introduced into the reaction by aspiration making flow rates difficult to control. They found that the morphology of the particles formed was a function of precursor concentration and residence time in the flame. Dopants and electric
20 fields were not used in the preparation of titanium dioxide.

 George, A.P., et al, *Farad. Symp. Chem. Soc.*, 7: 63 (1973), investigated titanium dioxide production in premixed flames and found that the product
25 particles had a self-preserving size distribution.

 Great Britain Patent Specification 2,252,707, Tioxide Group Services, Ltd., published August 12, 1992, describes a process for the decomposition of
degradable organic materials (e.g., chlorophenol) using UV light and a
photodecomposition catalyst which comprises a disk having anatase titanium
30 dioxide adhered to it. It is disclosed that the titanium dioxide preferably has a high surface area in the range from 20-200 m^2/gm . No process is disclosed for

making this titanium dioxide material. See also, U.S. Patent 5,163,626, Urwin, et al, issued November 17, 1992.

5 Ollis, et al, Environ. Sci. Technol., 25 (9): 1523 (1991), describes the use of photocatalysis to destroy contaminants in water. Titanium dioxide is taught to be an effective photocatalyst but there is little discussion of the physical characteristics of the titanium dioxide used. It is taught that the titanium dioxide used has a particle size of from 0.1 to 30 μm .

10 Okamoto, et al, Bull. Chem. Soc. Jpn., 58: 2023 (1985), discusses the photocatalytic decomposition of phenol using anatase titanium dioxide powder. The average particle diameter of the powder is between 0.76 and 1.88 μm .

15 U.S. Patent No. 4,892,712, Robertson, issued January 9, 1990, describes a reactor for fluid purification using photocatalysis. Anatase titanium dioxide is taught as being useful as a photocatalyst. However, there is no specific discussion of the physical characteristics of the titanium dioxide used, and specifically there is no discussion of surface area.

20 U.S. Patent No. 5,198,403, Brand, et al, issued March 30, 1993, discusses the production of a catalyst material using titanium dioxide which is completely or predominantly in the anatase phase and has a surface area of from 40 to 500 m^2/gm , preferably from 75 to 150 m^2/gm .

25 The introduction of ions into the reactants during production of carbon black has been taught to be effective in reducing the particle size of the product formed. The ions can be produced either by the addition of alkali metals to the reaction stream (Haynes, et al., Proceedings of the Seventeenth Symposium (International) on Combustion, The Combustion Institute, 1365 (1979)) or by using
30 an electric/magnetic field (Soviet Patent 1,781,260, issued December 15, 1992). Neither of these disclosures suggests that the presence of ions has any effect on the crystalline structure of the carbon black product.

It has also been suggested that by applying an electric field to ionize reactants before they enter the combustion area in the production of silicon dioxide, small particle size product may be produced. See, Soviet Patent 948,881, issued August 7, 1982, and Hardesty and Weinberg, Proceedings of the Fourteenth Symposium (International) on Combustion, The Combustion Institute, 907 (1973). There is no teaching in these disclosures that this technique would have any effect on the crystalline structure of the silicon dioxide product.

The production of titanium dioxide in a diffusion flame reactor using an electric field applied by fixed flat screen electrodes located outside the combustion area has been taught. See, Katz, et al., Proceedings of the Twenty-Third Symposium (International) on Combustion, The Combustion Institute, 1733 (1990). This research suggested that the use of such electric fields resulted in increased particle size of titanium dioxide.

SUMMARY OF THE INVENTION

The present invention relates to a process for preparing titanium dioxide powder comprising the steps of:


- a) mixing vapor phase $TiCl_4$ and O_2 in a reaction area;
- b) externally heating said mixture in said reaction area; and
- c) collecting the titanium dioxide powder formed.

It is preferred that this process be carried out in a diffusion flame reactor using combustion of a hydrocarbon fuel, particularly methane, to provide the flame. Preferably a dopant (such as $SiCl_4$) may be added to the reaction mixture to desirably effect the properties of the titanium dioxide produced. It is also preferred that the vapor phase $TiCl_4$ be added to the reaction by bubbling an inert gas, such as argon, through liquid $TiCl_4$ and directing that gas to the reaction area. In a particularly preferred embodiment, a corona electric field is located across the reaction area where the combustion takes place. The use of this electric field maximizes production of particles having high surface area and low rutile (high

anatase) content. The product made using the process of the present invention and the use of that product as a photocatalyst are also claimed herein. The process of the present invention, particularly the embodiment which utilizes the corona electric field, may be used to form a wide variety of ceramic powders and even metallic or alloy powders.

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a process for the synthesis of titanium dioxide powders by TiCl_4 oxidation/hydrolysis. In chemical terms, the reactions being carried out in the present invention are as follows:



The process defined herein consists of three basic steps: (1) mixing the reactants together, (2) externally heating the reaction mixture, and (3) collecting the titanium dioxide powder formed in the reaction. The precise details of these steps are set forth below. Although specific executions and examples are discussed in this application, it is envisioned that the present invention encompasses the full range of obvious variants of those specifically disclosed herein. All percentages and ratios given herein are "by weight" unless otherwise specified.

Mixing Step

The mixing step takes place in a reactor. This reactor may encompass any vessel or area in which the reactants (TiCl_4 , O_2 and the optional dopant) can be mixed in their vapor phase and heated externally. Flame reactors are a preferred class of such reactors. In a flame reactor the reactants are present in the vapor phase and are heated by a flame. An example of such a reactor is a pre-mixed flame reactor in which the various reactants are mixed together prior to being introduced into the flame where the reaction takes place. This type of reactor is known in the art and, for example, is described in George, A.P., et al, Farad.

Symp. Chem. Soc., 7:63 (1973), incorporated herein by reference. Another type of reactor is a turbulent reactor. Preferred for use in the present invention is a diffusion flame reactor (particularly a laminar diffusion flame reactor) because it provides a higher quality titanium dioxide product by allowing better control of the reaction conditions. Laminar diffusion flame reactors of the type useful in the present invention are described in Fotou, Pratsinis and Baron, Coating of Silica Fibers by Ultrafine Particles in a Flame Reactor, Chem. Eng. Sci., 49: 1651 (1994) (see especially Fig. 1 and the first paragraph of the Experimental section), and Formentil, et al., in Aerosols and Atmospheric Chemistry, G.M. Hidy, ed, Academic Press, New York, pages 45-55 (1972), both incorporated by reference herein. The laminar diffusion flame reactor generally consists of five concentric quartz tubes 1mm thick. The diameter of the central tube is 2mm and the spacing between successive tubes is 1mm. The number of concentric tubes in the reactor and their size can be varied depending upon the requirements of the particular reaction. The design of this reactor is similar to the torches employed in the manufacture of optical fibers as well as in the synthesis of fumed silica. See, Bautista, J.R., et al, J. Aerosol Sci. 22: 667 (1991).

The $TiCl_4$ reactant is introduced into the reactor in the vapor phase. Any method of providing $TiCl_4$ in the vapor phase will work in the present invention (e.g., aspiration or aerosolization). It is preferred, however, that the $TiCl_4$ vapor be generated by bubbling an inert gas through liquid $TiCl_4$ and directing that gas (containing $TiCl_4$ vapor) into the reaction area. This procedure allows for precise control of $TiCl_4$ flow rate and concentration in the reaction area. As used herein, the term "inert" means that the gas which is used is inert to chemical reactions with $TiCl_4$ and the other reactants defined herein. The gas is also preferably anhydrous. Preferred gases for use in this capacity include argon, nitrogen, helium, krypton, chlorine, and mixtures thereof. Particularly preferred for use in the present invention is argon.

When a laminar diffusion flame reactor is used in the present invention, the argon gas/ $TiCl_4$ vapor is preferably directed through the central tube of the flame

reactor. The gas TiCl_4 flow rates utilized in the process of the present invention are generally from about $100\text{cm}^3/\text{min}$ to about $300\text{cm}^3/\text{min}$, and preferably are from about $150\text{cm}^3/\text{min}$ to about $250\text{cm}^3/\text{min}$. This flow rate (together with the liquid TiCl_4 temperature) essentially defines the concentration of TiCl_4 which is present in the reaction area. The TiCl_4 vapor concentration ranges (in the reaction area) which are useful in the present invention are from about 7×10^5 mol/min to about 1×10^2 mol/min, and preferably are from about 1×10^4 mol/min to about 5×10^3 mol/min. The actual concentration of TiCl_4 vapor in the argon gas may be controlled by heating the TiCl_4 liquid through which the argon gas is bubbled. The higher the temperature utilized, the greater the TiCl_4 vapor concentration achieved. In this regard, it is preferred that the TiCl_4 through which the argon is flowed or bubbled has a temperature of from about 20°C to about 100°C .

The TiCl_4 /argon flow rate (together with the flow rates for oxygen, fuel and dopant, if used) helps determine the residence time of the reactants in the reaction area. This residence time affects the characteristics of the final titanium dioxide product formed. A higher flow rate results in a shorter residence time in the reaction area which results in a larger specific surface area for the product produced. This is counterbalanced by the fact that an increase in the TiCl_4 concentration in the reaction area will result in a decrease in the specific surface area of the product formed. Thus, residence time and TiCl_4 concentration must be balanced in order to obtain the desired titanium dioxide surface area.

The other required reactant utilized in the process of the present invention is oxygen gas. Oxygen may be introduced into the system in any form, such as pure oxygen, but is preferably introduced into the system as filtered air. Any conventional filtering process may be used. The oxygen is preferably directed into the diffusion flame reactor in the second tube (i.e., the tube immediately adjacent to the central tube which is carrying the TiCl_4 reactant). When filtered air is used, its flow rate into the reactor is generally from about 0.3 to about 5.5 l/min, preferably from about 0.5 to about 2.5 l/min. The higher the flow rate of the air

(oxygen) entering the reactor, the lower the residence time of the reactants in the reaction area and the larger the surface area of the titanium dioxide formed.

The reaction mixture which is utilized in the present invention may also optionally include a dopant material, in vapor phase, to positively affect the physical attributes of the titanium dioxide formed. The dopant may either be premixed with the $TiCl_4$ reactant prior to entry into the reaction area or the $TiCl_4$ reactant and the dopant may be mixed in the reaction area. It is preferred that the $TiCl_4$ reactant and the dopant be premixed before they are introduced in the reaction area. In a laminar diffusion flame reactor, therefore, it is preferred that the dopant vapor also be introduced into the central core of the reactor.

Dopants which are useful in the present invention include silicon, phosphorus, germanium, boron, tin, niobium, chromium, silver, gold, palladium, aluminum, and mixtures thereof. Preferably, these dopants are introduced into the system as chlorides although other compounds may be used as long as they are liquids, may be introduced into the reaction system in the vapor phase, and contain the desired dopant element defined above (e.g., organo-metallic compounds may be used). Some of these dopant compounds become oxides during the course of the reaction. The use of tin or aluminum in the reaction tends to promote the formation of rutile crystalline phase in the titanium dioxide product. On the other hand, the use of $SiCl_4$ as the dopant in the process of the present invention tends to maximize the presence of the anatase phase in the final product and also minimizes particle size (which accordingly maximizes the specific surface area of the final product). In selecting the amount of dopant to be used in the process, it is generally advisable to use the smallest amount of dopant which creates the desired effect. For example, it is preferred, when silicon tetrachloride ($SiCl_4$) dopant is used, that the reaction mixture contain from about 5% to about 10% $SiCl_4$ on a molecular basis when compared to the amount of $TiCl_4$ in the system. It is possible to use $SiCl_4$ levels outside of this range although the products produced by the reaction will not be optimal for photocatalysis use.

The dopant is generally introduced into the system in the same way that the $TiCl_4$ reactant is. Specifically, it is preferred that the vapor phase dopant be introduced by bubbling an inert gas (i.e., inert to the particular dopant and other reactants utilized in the process) through the liquid dopant and that the dopant vapor/gas then be directed into the reaction area. Preferred gases for use in that regard include argon, nitrogen, helium, krypton, chlorine, and mixtures thereof. Argon is particularly preferred. The concentration of the dopant material in the reaction zone will depend upon the flow rate of the gas used, as well as on the temperature of the dopant through which the gas is bubbled. In that regard, it is preferred that the flow rate of the argon through the dopant liquid be from about 3 to about $50 \text{ cm}^3/\text{minute}$, that the concentration of the dopant entering the reaction area be from about 7×10^{-6} to about $1.4 \times 10^{-4} \text{ mol/minute}$, and that the temperature of the dopant liquid through which the argon is flowed or bubbled be from about -13 to about 25°C .

Heating Step

Once the $TiCl_4$ vapor, the O_2 and the optional dopant are combined in the reaction area, they are heated via external heating of the reaction area. Any source of heat may be used in the present invention. For example, electrical resistance may be used to heat the reaction area. In a flame reactor (such as a diffusion flame reactor) the heat is provided by combustion. In the laminar diffusion flame reactor, a fuel is fed into the reactor in a sleeve which completely surrounds the reactants being fed into the reactor. Therefore, when the fuel is ignited in the reaction area it is burning essentially at the periphery of the reactants which are being mixed together in the center of the flame (i.e., the heating is external to the reaction area). It has been found that when this configuration is used (i.e., the fuel is fed into a laminar diffusion flame reactor in a sleeve which completely surrounds the reactants ($TiCl_4/O_2$) being fed into the reactor), a significant reduction in both particle size and rutile content of the product formed takes place. In addition, by using this configuration and manipulating the reaction

conditions to lower precursor concentrations, lower flame residence times and lower flame temperatures, very fine anatase titania powders can be produced.

It is preferred that the fuel used in the process of the present invention be a hydrocarbon material, preferably methane, acetylene, propane, ethane, ethylene, or mixtures thereof. Methane is the most preferred fuel for use herein. The flame which is utilized in the reaction should be as blue as possible indicating complete combustion of the fuel with very little soot present. The flame generally has a temperature between about 1100K and about 2000K.

10

The presence of water vapor in the reaction area promotes the formation of anatase phase in the titanium dioxide product formed and, therefore, is desirable in the present invention. Water vapor forms *in situ* during the combustion process which is one of the reasons why combustion is the preferred source of heat in the present invention. If a non-combustion heat source is used in the present invention, water vapor can be added to the reaction mixture through the reactor.

15

The fuel is introduced into the reaction area at a rate of from about 125 to about 400 cm³/min, preferably from about 150 to about 300 cm³/min. The higher the flow rates of the fuel and oxygen entering the reactor, the higher the temperature in the reaction area. Increased fuel and oxygen flow rates also decrease residence time. The effects of fuel (e.g., methane) flow on the final product are controllable but relatively complex. At relatively long residence times, the surface area of the powders formed decreases. At medium residence times, the methane flow rate has little effect on the particle size, while at short residence times, the surface area of the product formed increases with methane flow rate. The flame temperature increases with increasing methane flow rate resulting in a higher sintering rate of particles formed and, hence, the larger particle size (lower surface area). Thus, in general, higher flame temperatures result in both increased particle size and rutile content in the product produced.

20

25

30

Collection Step

5 The final step in the process of the present invention is the collection of the titanium dioxide powder formed. This may be done in many ways known in the art, such as by collection through a filter or on a drum. It is preferred that the powder be collected on a metal (e.g., steel or nickel) plate located just outside the reaction area and placed such that the gases flowing through the reaction area or the air currents around the flame direct the particles formed to the plate. It is preferred that the plate be located from about 3 and about 12 cm, more preferably from about 4 and about 10 cm, above the mouth of the burner. The particles formed may also be collected by a filter, such as a glass fiber filter, which may optionally be aided by a vacuum pump. The collection should take place at a temperature which is lower than the flame temperature.

15 In controlling the characteristics of the titanium dioxide powder formed by the process, it is important to note that there are essentially two key variables in the process: reaction temperature and residence time in the reaction area. The temperature is, of course, controlled in any conventional way (e.g., identity of fuel, flow rate of fuel, flow rate of oxygen). The residence time in the reaction area is controlled based upon flow rates of the TiCl_4 vapor, the oxygen, the fuel and the dopant (if used) into the reaction area: the higher the collective flow rates of these items, the shorter the residence time will be in the reaction area. When the reaction temperature is relatively low (i.e., from about 1100 to about 1500K) and/or the residence time is relatively short (i.e., from about 0.075 to about 0.1 second, a collective flow rate of from about 1900 to about 2800 cm^3/min), the titanium dioxide product formed generally will have a high anatase phase composition and a high surface area making it excellent for use as a photocatalyst. On the other hand, where the residence time of the reactants in the reaction area is relatively long (i.e., from about 0.12 to about 0.5 second, collective flow rate from about 500 to about 1500 cm^3/min), particularly where the reaction temperature is relatively high (i.e., from about 1100 to about 2000K, particularly

from about 1500 to about 2000K), the titanium dioxide formed contains a high rutile phase composition and a relatively low surface area.

5 In a particularly preferred embodiment of the present invention, a corona discharge electric field is located across the reaction area where the combustion takes place (i.e., where the particles are formed). This procedure allows for the formation of excellent quality titanium dioxide particles, having high surface area and low rutile (high anatase) content, without requiring the use of the dopant materials described above. The fact that this result can be achieved without using
10 dopants yields a process which is less costly than one which requires dopants, and produces a product which has a higher degree of purity than if dopants were used. This process can be applied broadly in vapor phase flame generation reactions to form metallic, alloy and ceramic particles, such as silica, titania, alumina, borides, nitrides and carbides. Examples of such materials include metals (iron, aluminum,
15 alloys) and ceramic oxides and their mixtures, such as tin oxide, aluminum oxide (alumina), silicon oxide (silica), chromium oxide, iron oxide, germanium oxide, vanadium oxide, zinc oxide, zirconium oxide, copper oxide or barium oxide. Mixed metal oxides, such as superconductors, can also be prepared. These materials are formed using vapor phase reactions known in the art with the improvement of forming the particles in the presence of a corona discharge electric
20 field. The process is especially useful in preparing silicon oxides and titanium dioxide, most especially titanium dioxide (titania) in the manner described in the present application.

25 The characteristics of the electric field utilized (e.g., its location, polarity and strength) can have a significant impact on the properties of the titanium dioxide formed. Specifically, the electric field must be a corona (i.e., a discharge of electricity between point electrodes caused when the voltage gradient between those electrodes exceeds a certain critical value) having field lines limited to a
30 narrow region. A broader electric field, such as one between two plate electrodes, will not provide the degree of control required to achieve the benefits of the present invention. The electrodes utilized in this embodiment of the present

invention are generally in the form of needles made of an electrically conducting material, such as stainless steel, carbon, tin, titanium, preferably stainless steel, which come to a sharp point (from about 25 to about 150 μm , preferably from about 50 to about 100 μm , in diameter) on at least one end. The use of smaller diameter needles permits the formation of the corona using lower voltages.

The electrodes are generally placed in a horizontal plane (i.e., parallel to the ground, such that the direction of the electric field is approximately perpendicular to the flow of the reactants), one on each side of the flame with a gap between them where the combustion takes place. Generally, the distance between the tips of the electrodes will be from about 30 to about 60 mm, preferably from about 35 to about 45 mm. The tips of the electrodes should be placed outside the flame to minimize corrosion of the electrode tip. Preferably the tip of each electrode is placed from about 4 to about 10 mm outside the flame. If the tips of the electrodes are placed too far apart, the voltage required to achieve the corona will be too great for practical use. The electrodes may be positioned anywhere on the vertical axis within the reaction (combustion) area. However, best results are obtained when the electrodes are placed at the same height as the hottest part of the flame (i.e., at the point where the ceramic (e.g., TiO_2) particles are actually being formed). This generally means that the electrodes are located from about 0.5 to about 30 mm, particularly from about 1 to about 20 mm, most preferably about 1 mm to about 5 mm, above the mouth of the burner. Positioning the electrodes closer to the burner mouth results in the formation of particles which are smaller (i.e., have increased surface area).

While not intending to be bound by theory, it is believed that the electric field operates on the reaction in the following manner. The metallic or ceramic (e.g., titanium dioxide) particles, as they are formed in the flame, are charged by the electric field. The interaction between the particle charges and the electric field repels the particles out of the high temperature area quickly resulting in a finer/smaller particle than would have been formed had the particle remained in the high temperature area for a longer period of time. The charged particles then

- 15 -

reagglomerate in a lower temperature area (for example, above the flame). This results in particles which are finer in size (thereby having a larger specific surface area) and which contain less rutile (and therefore more anatase) crystalline phase. In addition, the corona (particularly at higher voltages) acts to flatten the flame as a result of the corona wind effect. This results in shorter residence time in the flame which causes the formation of particles which are smaller in size and, in the case of TiO_2 , have a higher anatase content. It is useful to contrast this effect with the one described in Katz, et al, Proceedings of the Twenty-Third Symposium (International) on Combustion, The Combustion Institute, 1733-1738 (1990). In Katz, et al, the electric field was provided by flat metal screens which charged the reactants before they entered the reaction area. By the time the particles entered the reaction area the charges on them had dissipated to a significant extent. In addition, the placement of the electrodes in Katz, et al made the repulsion mechanism described above difficult, if not impossible, to achieve. It is interesting to note that Katz, et al, reported that the presence of the electric field made the particles formed larger.

The electric field used in this preferred embodiment may be unipolar (positive or negative) or bipolar. It is produced using a direct current. Any conventional DC power source may be used. To produce a unipolar corona, one electrode is connected to the DC power supply (either positive or negative) and the other electrode is connected to the ground. For a bipolar corona discharge, one electrode is connected to the positive DC power supply and the other electrode is connected to the negative DC power supply. The applied voltages useful in this embodiment of the present invention are from about 2 to about 15 kV, preferably from about 4 to about 12 kV. As the voltage increases within these ranges, the particles formed tend to be smaller and, in the case of TiO_2 , have a higher anatase content. The required (e.g., the minimum voltage required to get a corona and to get an effect on the reaction) and optimum voltages will, of course, vary depending upon the placement and distance between the electrodes, the composition of the electrodes and the specifics of the reaction involved. Generally, unipolar fields tend to give better results than bipolar fields. Where the

- 16 -

flame has positive charge characteristics, a positive electric field tends to give better results. When a flame has negative charge characteristics, a negative electric field tends to give better results.

5 In general, with both positive and negative electric fields, the rutile content of the particles formed decreases as the applied voltage increases. The specific surface area of the particles formed increases with increasing voltage between the electrodes (for both unipolar and bipolar fields).

10 By manipulating the conditions in the reaction of the present invention, and particularly the reaction temperature and residence time, titanium dioxide powders having a range of anatase phase compositions and specific surface areas can be formed thereby making them useful for a very wide variety of end uses. When the titanium dioxide materials are to be used as catalysts in photocatalysis
15 (photooxidation) reactions, the materials should have a high anatase phase content and a relatively high surface area. Preferred titanium dioxide materials for use in photocatalysis reactions contain at least about 80% anatase phase (up to about 100% anatase phase is possible using the reaction of the present invention) and a specific surface area of at least about 100m²/gm (preferably from about 100 to
20 about 200m²/gm, most preferably from about 110 to about 175m²/gm).

The following examples, which are meant to be illustrative only and are not intended to restrict the scope of the present invention, illustrate the process and the
25 products of the present invention.

EXAMPLES

Example 1

30 A diffusion flame reactor is used for synthesis of titanium dioxide powders by TiCl₄ oxidation/hydrolysis. The reactor consists of five concentric quartz tubes 1mm thick. The diameter of the central tube is 2mm and the spacing between successive tubes is 1mm.

- 17 -

5 Dry argon gas (Wright Brothers, 99.8%) is bubbled through a gas-washing bottle containing titanium tetrachloride (Aldrich, 99.9%) (temperature = 293K) and is directed through the central tube of the flame reactor. Air and methane are passed through the second and third tubes of the reactor, respectively. Titanium dioxide particles produced by hydrolysis and oxidation of $TiCl_4$ in the flame are thermophoretically collected on a 4" x 4" stainless steel plate. The plate is located 5cm above the mouth of the reactor.

10 A constant Ar flow rate of 200cm³/min through the $TiCl_4$ bubbler is used. The corresponding molar flow rate of $TiCl_4$ is 1.4×10^{-4} mol/min. A mass flow controller (MKS Instruments, Inc.) is used to measure the flow rate of the argon stream through the $TiCl_4$ bubbler. Rotameters are used for measuring the air, methane and Ar/ $SiCl_4$ flows. A 0.015" gauge Pt-Rh thermocouple (Omeca Engineering) insulated with a mullite sheath is used for measuring the flame temperature.

20 The phase composition of the collected particles is determined by X-ray diffraction (XRD) in a Siemens D500 diffractometer using CuK_{α} radiation. The weight fractions of the rutile and anatase phases in the samples are calculated from the relative intensities of the strongest peaks corresponding to anatase ($2\theta = 25.6$ for the (101) reflection of anatase) and rutile ($2\theta = 27.5$ for the (110) reflection of rutile) peaks as described by Spurr and Myers, Quantitative Analysis of Anatase-Rutile Mixtures with an X-ray Diffractometer, Analytical Chem., 29: 760 (1957). The specific surface area of the powders is determined by nitrogen adsorption (Gemini 2360, Micromeritics) at 77K with the BET method. Transmission Electron Microscopy (TEM) in a Phillips CM20 instrument is used for morphological analysis of the powders.

30 Titanium dioxide powders are synthesized at four flame conditions shown in Table 1, below, together with the corresponding measured flame temperatures and residence times. Table 2 shows the specific surface areas of the powders produced, as well as the rutile and anatase contents of those powders. Powders

- 18 -

produced at the various flame conditions are designated as F1, F2, F3 and F4. Powder F1 has the lowest specific surface area (35m²/g) because of the longer residence time of the particles in the flame. Long residence times at the high flame temperatures cause coalescence of the newly formed aggregates, resulting in larger primary particles and, consequently, loss of specific surface area. Short residence times and low flame temperatures, on the other hand, favor the formation of smaller primary particles resulting in high surface area powders. Powder F1 has the highest rutile content (13%) of the powders made, while powders F2 and F3 contain very little rutile phase and powder F4 is almost completely anatase. The powder F4, because of its high surface area and its very high anatase content, is an excellent photocatalyst, for example, in the photooxidation of phenol.

TABLE 1

Flame #	CH ₄ Flow Rate (cm ³ /min)	Air Flow Rate (l/min)	Flame Temperature (K)	Residence Time x 10 ³ sec
1	160	0.500	1178	277
2	208	1.174	1300	136
3	277	1.433	1340	122
4	277	2.314	1440	75

TABLE 2


Powder	BET Area (m ² /g)	Rutile Content (wt %)	Anatase Content (wt %)
F1	35	13	87
F2	54	7	93
F3	78	6.5	93.5
F4	110	<0.1	>99.9

- 19 -

Photocatalytic experiments are performed using the F4 titanium dioxide prepared above as the catalyst and phenol as the target molecule. Aqueous solutions of phenol of initial nominal concentration of 1mM are employed. The reactor working volume is 600 cm³. The pH of the solutions is controlled at 3.5 in the beginning of the reaction. The UV-light source used is a 450 W medium pressure, mercury vapor, quartz lamp (Hanovia). The lamp is placed inside a quartz cooling jacket immersed in the solution inside the reaction vessel. The TiO₂ powder concentration in the solution is 0.5 g/L. The temperature of the solution is controlled in the range 35-40 °C. The concentration of phenol in the solution is monitored for a period of 120 minutes with a UV-light spectrophotometer.

A 50% reduction of phenol concentration is obtained in less than 2 hours without bubbling oxygen in the solution when the F4 titanium dioxide powder is used. This represents excellent photocatalysis performance.

Irradiation of TiO₂ particles with UV light in the wavelength range of 300-400 nm provides pairs of holes and electrons. These react with adsorbed species on the titanium dioxide surface and form reactive hydroxyl radicals. The latter oxidize phenol according to the following reaction:



Example 2

Using the apparatus and the analytical methods described in Example 1 silicon-doped titanium dioxide is prepared as follows. Argon gas is bubbled through SiCl_4 (Aldrich, 99.9%) in a gas-washing bottle and is mixed with the TiCl_4 laden argon stream. The temperature of the SiCl_4 and argon flow rate can be varied to vary the SiCl_4 concentration. The Ar/TiCl_4 and Ar/SiCl_4 streams are premixed before they are introduced into the flame. The gas mixture is carried into the flame for the reaction. The vapor pressure of SiCl_4 at room temperature is much higher than that of TiCl_4 . In order to introduce small amounts, the temperature of SiCl_4 is maintained at -11 ± 1 °C using ice-sodium chloride mixture. The concentrations of TiCl_4 and SiCl_4 in the gas stream are determined by recording the weight of the halides before and after each experiment that is carried out while argon is bubbled through the halide at constant flow rate. For example, the $\text{SiCl}_4/\text{TiCl}_4$ molar ratio in the reaction area (based on mol % of TiCl_4), is 5%, 10%, 15% and 20%. The rutile content of the powders obtained in such a reaction tends to decrease by increasing the amount of SiCl_4 introduced into the flame. Hence, doping with Si can be used, with appropriate process conditions and controls, to increase the anatase content and specific surface area of the titanium dioxide powders formed, thereby increasing the ability of those powder to act as photocatalyst.

Example 3

Using the apparatus and reaction conditions described in Example 1, TiO_2 is synthesized (without the use of dopants) in the presence of a corona electric field in accordance with a preferred embodiment of the present invention. In this example, the following reaction conditions are utilized:

CH_4 flow rate = 160 cm^3/min .
Air flow rate = 0.5 l/min.
 TiCl_4 molar flow rate = 1.4×10^{-4} mol/min.
Flame temperature = 1178K
Residence Time = 0.05 - 0.2 second (average = 0.1 second)

The needle electrodes used to generate the corona discharge are made of stainless steel, are 5 cm in length and come to a sharp point (50 - 100 μ m in diameter) at one end. For a unipolar corona discharge, one electrode is connected to the power supply and the other electrode is connected to the ground. For a bipolar corona discharge, one electrode is connected to the positive DC power supply and the other electrode is connected to the negative DC power supply. The power supplies used are manufactured by Spellman and by Gamma High Voltage, Inc. The electrodes are positioned horizontally, 1 cm above the mouth of the burner. The distance between the electrodes is 4 cm and the tip of each electrode is about 6 mm away from the flame. A corona is observed between the electrodes when the applied voltage is above 4 kV. The voltage is varied between 0 and 10 kV in the context of positive, negative and bipolar fields. The titanium dioxide powder samples are collected onto a nickel plate 7 cm above the mouth of the burner. The specific surface area and rutile content of the powders formed are measured as described in Example 1. The following results are obtained.

Applied Voltage (kV)	Negative Polarity		Positive Polarity		Bipolar
	Specific Surface Area (m ² /g)	Rutile Content (wt. %)	Specific Surface Area (m ² /g)	Rutile Content (wt. %)	Specific Surface Area (m ² /g)
0	35	17.5	35	17.5	35
4	44	17	42.5	16	
5	55	10	61		46
6	72	9	70	7	
7					66
8	73	6	75	7	
9	74	7.5			
10			76	6.5	

Example 4

A premixed flame reactor is used for the synthesis of silica and tin oxide powders by the oxidation/hydrolysis of their respective halides (SiCl_4 or SnCl_4). SiCl_4 is kept at 273 K due to its high vapor pressure and SnCl_4 is kept at room temperature (293 K). The reactor is made of alumina with an inside diameter of 0.5" (1.27 cm). The reactants (methane, air and the carrier gas Argon with the precursor) are mixed before they enter the flame. The needle electrodes are placed at 0.1 and 1.0 cm from the tip of the burner. The distance between the tips of the needles is fixed at 4 cm. The corona between the needles is created using a positively polar DC power supply (Speilman). The powders are collected on a glass fiber filter (Gelman Scientific) positioned at 11.5 cm from the tip of the reactor. The specific surface area of silica and titania powders is obtained as described in Example 1. The experimental conditions and the results obtained are shown below:

Methane : 237 cm^3/min
 Air : 1095 cm^3/min
 Argon : 200 cm^3/min

Silica

Precursor (SiCl_4) flow rate: 8.3×10^{-4} mol/min

Specific surface area, m^2/g

Needle position from the burner tip

Potential, kV	0.1 cm	1.0 cm
0	129	129
5		127
6	171	144
7	215	
8	215	207
9		219

- 23 -

Tin oxide

Precursor (SnCl_4) flow rate: 2.6×10^{-4} mol/minSpecific surface area, m^2/g

Needle position from the burner tip

5

10

Potential, kV	0.1 cm	1.0 cm
0	13	13
5	13	14
6	16	13
8	19	16
9	23	16
10	34	17
11		18

WHAT IS CLAIMED IS:

1. A process carried out in a flame reactor for preparing titanium dioxide powder comprising the steps of:
 - a) mixing vapor phase TiCl_4 and O_2 in a reaction area;
 - b) externally heating said mixture in said reaction area using a flame which is formed by combustion of a hydrocarbon fuel; and
 - c) collecting the titanium dioxide powder formed.
2. A process according to Claim 1 wherein the flame reactor is a laminar diffusion flame reactor.
3. A process according to Claim 2 wherein said vapor phase TiCl_4 is fed into the center core of said diffusion flame reactor.
4. A process according to Claim 3 wherein said vapor phase TiCl_4 is formed by bubbling an inert gas through TiCl_4 liquid.
5. A process according to Claim 4 wherein said gas is selected from the group consisting of argon, nitrogen, krypton, helium, chlorine, and mixtures thereof.
6. A process according to Claim 5 wherein the gas flow rate of the TiCl_4 vapor is from about 100 to about 300 cm^3/min and the concentration of TiCl_4 entering the reactor is from about 7×10^{-5} to about 1×10^{-2} mol/min.
7. A process according to Claim 6 wherein the O_2 is fed into a sleeve of said diffusion flame reactor adjacent to the center core.

- 25 -

8. A process according to Claim 7 wherein the O_2 is introduced as air having a flow rate is from about 0.3 to about 5.5 l/min.
9. A process according to Claim 3 wherein the fuel is fed into said diffusion flame reactor in a sleeve which surrounds the sleeves carrying the vapor phase $TiCl_4$ and the O_2 .
10. A process according to Claim 9 wherein the flow rate of said fuel into the reactor is from about 125 to about 400 cm^3/min .
11. A process according to Claim 10 wherein the fuel is selected from the group consisting of methane, acetylene, propane, ethane, ethylene, and mixtures thereof.
12. A process according to Claim 11 wherein the flame has a temperature of from about 1100K to about 2000K and is blue indicating substantially complete combustion of the fuel.
13. A process according to Claim 12 wherein the fuel is methane and the carrier gas for $TiCl_4$ is argon.
14. A process according to Claim 13 which is carried out under low temperature (about 1100 to about 1500 K) and a short residence time in the reaction area (about 0.075 to about 0.1 seconds).
15. A process according to Claim 14 wherein the argon flow rate is from about 150 to about 250 cm^3/min and the $TiCl_4$ concentration in the reaction area is from about 1×10^{-4} to about 5×10^{-3} mol/min.

- 26 -

16. A process for preparing titanium dioxide powder comprising the steps of:
- 5 a) mixing in a reaction area vapor phase TiCl_4 , O_2 and a dopant selected from the group consisting of compounds of silicon, phosphorus, germanium, boron, tin, aluminum, niobium, chromium, silver, gold, palladium, and mixtures thereof;
- b) externally heating said mixture in said reaction area; and
- c) collecting the titanium dioxide powder formed.
17. A process according to Claim 16 which is carried out in a laminar diffusion flame reactor and wherein said dopant is selected from the group consisting of chlorides of silicon, phosphorus, germanium, boron, tin, aluminum, niobium, chromium, silver, gold, palladium, and mixtures thereof.
- 5 18. A process according to Claim 17 wherein the mixture is heated by a flame which is formed by combustion of a hydrocarbon fuel.
19. A process according to Claim 18 wherein the dopant is silicon tetrachloride.
20. A process according to Claim 19 wherein the reaction mixture contains from about 5% to about 10% SiCl_4 on a molecular basis compared to the amount of TiCl_4 .
21. A product made according to the process of Claim 1.
22. A product made according to the process of Claim 14.
23. A product made according to the process of Claim 16.
24. A product made according to the process of Claim 20.

- 27 -

25. A photooxidation reaction which utilizes the compound of Claim 21 as a catalyst.
26. A photooxidation reaction which utilizes the compound of Claim 23 as a catalyst.
27. A photooxidation reaction which utilizes the compound of Claim 24 as a catalyst.
28. A process according to Claim 1 wherein across said reaction area is a corona electric field having a voltage from about 2 to about 15 kV.
29. A process according to Claim 28 wherein the flame reactor is a laminar diffusion flame reactor.
30. A process according to Claim 29 wherein the corona electric field is formed between two needle electrodes horizontally positioned on opposite sides of the flame at a height above the mouth of the burner which corresponds to the hottest area of the flame.
31. A process according to Claim 30 wherein the distance between the opposing tips of the electrodes is from about 30 to about 60 mm.
32. A process according to Claim 31 wherein the electrodes are placed from about 0.5 to about 30 mm above the mouth of the burner.
33. A process according to Claim 32 wherein the voltage of the electric field is from about 4 to about 12 kV.

34. A process according to Claim 33 wherein the electric field is unipolar.
35. A process according to Claim 11 wherein across said reaction area is a corona electric field having a voltage from about 2 to about 15 kV.
36. In a process for forming metallic or ceramic particles in a vapor phase reaction the improvement wherein the particles are formed in the presence of a corona discharge electric field.
37. A process according to Claim 36 wherein ceramic particles selected from the group consisting of silica, titania, alumina, zirconia, zinc oxide, tin oxide, germania, borides, nitrides, carbides and mixtures thereof are formed.
38. A process according to Claim 37 wherein the ceramic particles formed are selected from the group consisting of silica, titania and tin oxide.
39. A process according to Claim 38 wherein the corona discharge electric field is formed between needle electrodes.
40. A process according to Claim 39 wherein the distance between said electrodes is from about 30 to about 60 mm.
41. A process according to Claim 40 wherein the corona discharge electric field has a voltage of from about 4 to about 12 kV.
42. A process according to Claim 41 wherein the reaction is carried out in a reactor selected from the group consisting of premixed flame reactors, turbulent flame reactors and laminar diffusion flame reactors.

43. A process according to Claim 42 wherein the reaction is carried out in a laminar diffusion flame reactor.

INTERNATIONAL SEARCH REPORT

 Intern. Application No.
PCT/US 95/10841

A. CLASSIFICATION OF SUBJECT MATTER		
IPC 5	C01G23/07	C01B13/28 C01G19/02 C01B33/00
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC 6 C01G C01B		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB,A,707 389 (G.L.CABOT) 23 November 1949 see the whole document ---	1-3,9, 11,12, 16,18
X	GB,A,916 250 (AMERICAN CYANAMID COMP) 20 November 1959 see page 2 - page 7 ---	1-3,11, 16-24
X	PATENT ABSTRACTS OF JAPAN vol. 007 no. 061 (C-156), 15 March 1983 & JP,A,57 209845 (NIPPON DENSHIN DENWA KOSHA) 23 December 1982, see abstract ---	4,5
X	EP,A,0 595 078 (DEGUSSA AG) 4 May 1994 see page 5 ---	25-27
-/-		
<input checked="" type="checkbox"/> X	Further documents are listed in the continuation of box C.	
<input checked="" type="checkbox"/> X	Patent family members are listed in annex.	
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, etc. exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" Inter document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "A" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
12 December 1995		27. 12. 95
Name and mailing address of the ISA European Patent Office, P.B. 3818 Patentstein 2 NL - 2280 HV Rijswijk Tel. (+ 31-70) 340-2040, Telex 31 681 epo nl, Fax: (+ 31-70) 340-3016		Authorised officer LIBBERECHT, E

INTERNATIONAL SEARCH REPORT

Internat. Application No.
PCT/US 95/10841

C.(Communication) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,3 419 351 (H. ZIRINGIBL) 31 December 1968 see the whole document	28,36-38
A	US,A,3 414 379 (R.J. WIGGINTON) 3 December 1968 see the whole document	28,36,42
A	GB,A,1 105 605 (BRITISH TITAN PRODUCTS) 29 April 1964 see the whole document	1,16,28,37

INTERNATIONAL SEARCH REPORT

 Internat. Application No.
 PCT/US 95/10841

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-707389		NONE	
GB-A-916250		NONE	
EP-A-595078	04-05-94	DE-A- 4235936 JP-A- 6101848 US-A- 5451390	28-04-94 12-07-94 19-09-95
US-A-3419351	31-12-68	NONE	
US-A-3414379	03-12-68	BE-A- 664882 DE-A- 1592945 FR-E- 88609 GB-A- 1111411 NL-A- 6507087	01-10-65 17-12-70 26-05-67 05-12-65
GB-A-1105605		BE-A- 663194 CA-A- 944930 DE-A- 1542619 FR-A- 1449664 NL-A- 6505553	29-10-65 09-04-74 02-07-70 14-11-66 01-11-65